

Burgdorf, 06.06.2018

#### Test order No. 2018-061

Date of order: 23.05.2018

Responsible:

Pages: 2

#### Methoden:

AATCC 30-2017 Part III Qualitative test for determination of the antimycotic

effectiveness:

JIS L 1902:2015 Quantitative analysis for determination of the

bacteriostatic activity:

# **SANITIZED AG**

Erich Rohrbach Head Microbiology

The findings are valid for the tested object(s) only. Filing record of report and documentation is 10 years.

# SANITIZED AG

#### **Results**

# **Description of sample**

Sample number: 2018-061-01 Received: 23.05.2018
Business: TEXTILE Type: QC

Identification: Textil Batavia - Art. B2100002125

Main Component: 100% PES Appearance: White

Field of Application: Hospital courtains

Sanitized Products: Sanitized® TH 22-27

Declared quantity: 40g/l

Finishing Process(es): Padding (pickup: 50%)

Finishing Parameter(s): Drying: 150°C

Remark: Production sample

# Test results of the SANITIZED-laboratory

# Qualitative test for determination of the antimycotic effectiveness:

Method	Test point	Growth	Halo in mm	Evaluation
AATCC 30-2017 Part III	Aspergillus niger ATCC 6275	None	-	Good effect

# Quantitative analysis for determination of the bacteriostatic activity:

Method	Test point	Activity	Reduction in %	Evaluation
JIS L 1902:2015	Staphylococcus aureus (MRSA) ATCC 33592	3.50	99.97	Good effect

Test order No.: 2018-061